FOUNDATION Geotextiles

256 Paper Lane, Clarkesville, GA 30523, Tel 706/839-6632, fax 706/839-6634, Sales@foundationgt.com

Technical Data Sheet

FG57

Foundation Geotextiles FG57 is manufactured from high-tenacity polypropylene yarns, which are woven into a dimensionally stable network in such a manner that the yarns retain their relative position to one another. FG57 resists ultraviolet deterioration and biological degradation and is inert to most naturally encountered soil chemicals, alkalis, and acids. NTPEP certified fabric.

Property	Test Procedure	UNIT	MARV
Grab Tensile Strength	ASTM D-4632	Lbs	500 x 475
		kN	(2.2 x 2.1)
Grab Elongation	ASTM D-4632	percent	11 x 4
Wide Width Tensile	ASTM D-4595	Lbs/ft	4800 x 4800
		(kN/m)	(70 x 70)
Wide Width Tensile @ 5%	ASTM D-4595	Lbs/ft	2400 x 3000
		(kN/m)	(35 x 43.8)
Trapezoidal Tear	ASTM D-4533	Lbs	180 x 180
		(kN)	(.80 x .80)
Flow Rate	ASTM D-4491	Gal/min/ft ²	36
		(l/m/m²)	(1466)
Permittivity	ASTM D-4491	Sec ~1	0.50
Apparent Opening Size	ASTM D-4751	US Sieve	30
(AOS)		(mm)	(0.60)
UV Resistance (@500 hrs)	ASTM D-4355	%	80
		Strength	
		Retained	
CBR	ASTM D-6241	Lbs	2000
		(kN)	(8.9)

Standard Roll Length 15x300 ft

MARV: Minimum average roll value

Note: Minimum average roll values represent a 97.5% confidence level, calculated as the mean minus two standard deviations.

This information is provided for reference purposes only and is not intended as a warranty or guarantee. Foundation Geotextiles assumes no liability in connection with the use of this information.